

# Red-emitting magnetic mesocomposites of Ag-decorated Fe<sub>3</sub>O<sub>4</sub>@SiO<sub>2</sub> nanoflowers coated with Y<sub>2</sub>O<sub>3</sub>:Eu<sup>3+</sup>: Study of iron oxide induced luminescence quenching

Latif Ullah Khan<sup>1,2</sup>, Hermi Felinto Brito<sup>2</sup>, Diego Muraca<sup>1</sup>, Luelc Sousa da Costa<sup>1</sup>, Maria Cláudia França da Cunha Felinto<sup>3</sup>

<sup>1</sup>Centro Nacional de Pesquisa em Energia e Materiais, <sup>2</sup>Instituto de Química, Universidade de São Paulo, <sup>3</sup>Instituto de Pesquisas Energéticas e Nucleares

*e-mail: latifkhn@iq.usp.br*

The new multistep approach for co-assembling magnetic iron oxide nanoflowers with red-emitting Y<sub>2</sub>O<sub>3</sub>:Eu<sup>3+</sup> to form magneto-luminescent mesocomposites was reported. The Fe<sub>3</sub>O<sub>4</sub> core particles prepared by solvothermal method were layered with SiO<sub>2</sub> shell and decorated with small size spherical Ag nanoparticles as well as further coated with Y<sub>2</sub>O<sub>3</sub>:Eu<sup>3+</sup> luminophore. The nanoflower shape Fe<sub>3</sub>O<sub>4</sub> core of size ~110 nm and crystalline cubic structure of bifunctional iron-oxide@Y<sub>2</sub>O<sub>3</sub>:Eu<sup>3+</sup>, Fe<sub>3</sub>O<sub>4</sub>@SiO<sub>2</sub>@Y<sub>2</sub>O<sub>3</sub>:Eu<sup>3+</sup> and Fe<sub>3</sub>O<sub>4</sub>@SiO<sub>2</sub>-Ag@Y<sub>2</sub>O<sub>3</sub>:Eu<sup>3+</sup> (1 mol%) mesocomposites were confirmed from X-rays diffraction, EDS spectra and transmission electron microscopy images. The static magnetic measurements supported and manifested nonsuperparamagnetic behavior of the materials at 300 K. The iron oxides are usually luminescent quencher, therefore, the photoluminescence properties based on the emission spectral data and luminescence decay curves were studied. In addition, experimental intensity parameters ( $\Omega_\lambda$ ), lifetimes ( $\tau$ ), emission quantum efficiencies as well as radiative ( $A_{\text{rad}}$ ) and non-radiative ( $A_{\text{nrad}}$ ) decay rates were also calculated, in order to probe the local chemical environment of the Eu<sup>3+</sup> ion and better understand the phenomena of iron oxide induced luminescence quenching. The highest value of the quantum efficiency = 74 %, for the a-Fe<sub>2</sub>O<sub>3</sub>@Y<sub>2</sub>O<sub>3</sub>:Eu<sup>3+</sup> (1 mol%) among all the luminescent and magnetic mesocomposites suggests that Fe<sub>2</sub>O<sub>3</sub> is induced lower luminescence quenching than Fe<sub>3</sub>O<sub>4</sub>. Though, the thin layer of SiO<sub>2</sub> spacer is caused of increase the quantum efficiency, whereas the Ag is further enhanced the luminescence quenching by energy transfer from Eu<sup>3+</sup> ion to the Ag nanoparticles. These novel Eu<sup>3+</sup> mesocomposites may act as a red emitting layer for magnetic and light converting molecular devices.